



Anc. Ets.

STOOPEN & meeûs

SINCE
1894

TECHNICAL DATASHEET : StucProtect

DESCRIPTION:

StucProtect is a waterborne, solvent-free emulsion to protect STUC Deco, STUC Granito, lime paint and lime stucco. StucProtect has protective and hydrophobic properties and is not film-forming.

Suitable for indoor and outdoor use. StucProtect can be removed with a pressure washer or alkaline cleaner. StucProtect has little effect on the colour and gives little shine.

PACKAGING:

StucProtect comes in packs of 5 liters.

TECHNICAL SPECIFICATIONS:

Form of delivery:	white liquid
Odor:	mild
Number of layers:	1 or 2 layers
Consumption:	approx 1 liter / 15 m ² in two layers, depending on the porosity of the surface.
Drying time:	touch dry after 2 hours (depending on weather conditions)
pH:	9
Density:	1
Temperature:	Surface temperature > +5 ° C processing temperature from +5 ° C to +25 ° C
Shelf Life:	Two years if stored in a sealed container in a cool, frost-free environment
Tools:	paint roller
Tool cleaning:	water

SURFACE:

STUC Deco & STUC Granito, lime paint and lime stucco. The surface should be completely dry.

INSTRUCTIONS:

Recommended Tools: paint roller

Stir well before use.

Apply with roller without dilution.

StucProtect is applied in 1 to 2 thin layers, crossed with a paint roller without rolling out too long. This is to avoid to further roll out product that has already been absorbed in order to prevent white haze forming on the surface.

Dry after 2 hours. Waiting time between 2 layers, + / - 2 hours.

Protection check after 2 hours by moistening the surface with slightly humid sponge.

PRECAUTIONS:

Keep from freezing.

The product is 100% VOC free and contains 0 grams. per liter of organic solvents.

NOTE:

Stoopen & Meeûs guarantees the highest quality of its products, however it does not accept any liability for the improper application of its products.

Anc. Ets. Stoopen & Meeûs

Van Praetstraat, 22

B-2660 Hoboken

Tel. 32 3 825 00 55

Site : www.stoopen-meeus.com

Email : dragon@stoopen-meeus.com

Revisedatum : 28/11/2011